

Taiwan Sheen Soon Sheenthane® A9550 Thermoplastic Polyurethane Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyurethane TPE , Polyurethane, TP , Thermoplastic Polyurethane, Elastomer, Ether Grade

Material Notes:

Thermoplastic polyurethane elastomer for injection moldingPolyether gradeInformation provided by Taiwan Sheen Soon Co., LTD.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Taiwan-Sheen-Soon-Sheenthane-A9550-Thermoplastic-Polyurethane-Elastomer.php

Physical Properties	Metric	English	Comments
Density	1.16 g/cc	0.0419 lb/in ³	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	93 - 97	93 - 97	
Tensile Strength	39.2 MPa	5690 psi	
Elongation at Break	450 %	450 %	
100% Modulus	0.01224 GPa	1.775 ksi	
300% Modulus	0.0221 GPa	3.20 ksi	

Processing Properties	Metric	English	Comments
Processing Temperature	190 - 210 °C	374 - 410 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China