

Techmer ES Elastoblend® PA6/6 GF8 IM3 BK 8% Glass Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 10% Glass Fiber Filled , Nylon 66, Glass Reinforced, Impact Grade , Nylon 66, Heat Stabilized

Material Notes:

Availability: North America Forms: Pellets Filler/Reinforcement: Glass Fiber Reinforcement, 8% Filler by Weight Additive: Heat Stabilizer, Lubricant and Impact Modifier Features: Heat Stabilized, Lubricant and Impact Modified Processing Method: Injection Molding Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-Elastoblend-PA66-GF8-IM3-BK-8-Glass-Filled.php

Physical Properties	Metric	English	Comments
Density	1.16 g/cc	0.0419 lb/in ³	ASTM D792
Water Absorption	0.80 % @Time 86400 sec	0.80 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0080 cm/cm @Thickness 3.17 mm	0.0080 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	111	111	ASTM D785
Tensile Strength, Yield	77.2 MPa	11200 psi	ASTM D638
Elongation at Break	4.0 %	4.0 %	ASTM D638
Flexural Strength	103 MPa	15000 psi	ASTM D790
Flexural Modulus	2.76 GPa	400 ksi	ASTM D790
Izod Impact, Notched	1.17 J/cm @Thickness 3.17 mm	2.20 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	54.0 Åµm/m-Å°C	30.0 Åµin/in-Å°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	252 Å°C	485 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	220 Å°C	428 Å°F	Unannealed; ASTM D648
Flammability, UL94	HB @Thickness 1.50 mm	HB @Thickness 0.0591 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+14 ohm-cm	1.00e+14 ohm-cm	ASTM D257
Dielectric Strength	19.3 kV/mm	490 kV/in	Method A (Short-Time); ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China