

Techmer ES Electrablend® ABS CF10 A1 10% Carbon Filled

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), 10% Carbon Fiber Filled

Material Notes:

Availability: North America Forms: Pellets Filler/Reinforcement: Carbon Fiber, 10% Filler by Weight Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-Electrablend-ABS-CF10-A1-10-Carbon-Filled.php

Physical Properties	Metric	English	Comments
Density	1.09 g/cc	0.0394 lb/in ³	ASTM D792
Water Absorption	0.14 % @Time 86400 sec	0.14 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.010 cm/cm @Thickness 3.17 mm	0.010 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	108	108	ASTM D785
Tensile Strength, Yield	82.7 MPa	12000 psi	ASTM D638
Elongation at Break	1.5 %	1.5 %	ASTM D638
Flexural Strength	117 MPa	17000 psi	ASTM D790
Flexural Modulus	6.14 GPa	890 ksi	ASTM D790
Izod Impact, Notched	0.641 J/cm @Thickness 3.17 mm	1.20 ft-lb/in @Thickness 0.125 in	ASTM D256
Izod Impact, Unnotched	1.60 J/cm @Thickness 3.17 mm	3.00 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	37.8 Åµm/m-Å°C	21.0 Åµin/in-Å°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	113 Å°C	235 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	104 Å°C	220 Å°F	Unannealed; ASTM D648
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1000 - 1.00e+6 ohm-cm	1000 - 1.00e+6 ohm-cm	ASTM D257
Surface Resistance	100 - 10000 ohm	100 - 10000 ohm	ASTM D257

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China