

Techmer ES Electrablend® ABS CF30 BK 30% Carbon Filled

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), 30% Carbon Fiber Filled

Material Notes:

Availability: North AmericaForms: PelletsFiller/Reinforcement: Carbon Fiber, 30% Filler by WeightAppearance: BlackInformation provided by TP Composites, Inc.

Order this product through the following link:
http://www.lookpolymers.com/polymer_Techmer-ES-Electrablend-ABS-CF30-BK-30-Carbon-Filled.php

Physical Properties	Metric	English	Comments
Density	1.19 g/cc	0.0430 lb/in ³	ASTM D792
Water Absorption	0.14 %	0.14 %	ASTM D570
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Flow	0.0015 cm/cm	0.0015 in/in	ASTM D955
	@Thickness 3.17 mm	@Thickness 0.125 in	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	110 MPa	16000 psi	ASTM D638
Elongation at Yield	4.0 %	4.0 %	ASTM D638
Flexural Yield Strength	138 MPa	20000 psi	ASTM D790
Flexural Modulus	12.4 GPa	1800 ksi	ASTM D790
Izod Impact, Notched	0.534 J/cm	1.00 ft-lb/in	ASTM D256
	@Thickness 3.17 mm	@Thickness 0.125 in	
Izod Impact, Unnotched	2.67 J/cm	5.00 ft-lb/in	ASTM D256
	@Thickness 3.17 mm	@Thickness 0.125 in	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	19.8 Åµm/m-Å°C	11.0 Åµin/in-Å°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	113 Å°C	235 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	104 Å°C	220 Å°F	Unannealed; ASTM D648
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Surface Resistance Electrical Properties	4500 ohm Metric	4500 ohm English	ASTM D257 Comments
---	--------------------	---------------------	-----------------------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China