

Techmer ES HiFill FR[®] PA6/6 FR 346 RD

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Heat Stabilized , Nylon 66, Unreinforced, Flame Retardant

Material Notes:

Availability: North America Forms: Pellets Additive: Lubricant and Heat Stabilizer Features: Flame Retardant, Heat Stabilized and Lubricated Appearance: Red Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-FR-PA66-FR-346-RD.php

Physical Properties	Metric	English	Comments
Density	1.22 g/cc	0.0441 lb/in ³	ASTM D792
Water Absorption	0.90 % @Time 86400 sec	0.90 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.018 cm/cm @Thickness 3.17 mm	0.018 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	115	115	ASTM D785
Tensile Strength, Yield	62.1 MPa	9000 psi	ASTM D638
Elongation at Break	60 %	60 %	ASTM D638
Flexural Strength	91.0 MPa	13200 psi	ASTM D790
Flexural Modulus	0.255 GPa	37.0 ksi	ASTM D790
Izod Impact, Notched	0.694 J/cm @Thickness 3.17 mm	1.30 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	91.8 Åµm/m-Å°C	51.0 Åµin/in-Å°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	204 Å°C	400 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	62.8 Å°C	145 Å°F	Unannealed; ASTM D648
Flammability, UL94	V-0 @Thickness 0.800 mm	V-0 @Thickness 0.0315 in	
	5VB @Thickness 2.00 mm	5VB @Thickness 0.0787 in	

Thermal Properties	Metric	English	Comments
Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+14 ohm-cm	1.00e+14 ohm-cm	ASTM D257
Surface Resistance	1.00e+15 ohm	1.00e+15 ohm	ASTM D257
Dielectric Strength	27.2 kV/mm	690 kV/in	Method A (Short-Time); ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China