

Techmer ES HiFill FR[®] PA6/6 GF25 FR-N IM3 BK 25% Glass Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Glass Fiber Filled , Nylon 66, Impact Grade

Material Notes:

Availability: North America Forms: Pellets Filler/Reinforcement: Glass Fiber, 25% Filler by Weight Additive: Impact Modifier Features: Flame Retardant, Halogen Free and Impact Modified Appearance: Black Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-FR-PA66-GF25-FR-N-IM3-BK-25-Glass-Filled.php

Physical Properties	Metric	English	Comments
Density	1.34 g/cc	0.0484 lb/in ³	ASTM D792
Water Absorption	0.95 % @Time 86400 sec	0.95 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0030 cm/cm @Thickness 3.17 mm	0.0030 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	94	94	ASTM D785
Tensile Strength, Yield	152 MPa	22000 psi	ASTM D638
Elongation at Break	3.0 %	3.0 %	ASTM D638
Flexural Strength	200 MPa	29000 psi	ASTM D790
Flexural Modulus	7.58 GPa	1100 ksi	ASTM D790
Izod Impact, Notched	0.694 J/cm @Thickness 3.17 mm, Temperature -40.0 Â°C	1.30 ft-lb/in @Thickness 0.125 in, Temperature -40.0 Â°F	ASTM D256
	1.07 J/cm @Thickness 3.17 mm, Temperature 22.8 Â°C	2.00 ft-lb/in @Thickness 0.125 in, Temperature 73.0 Â°F	ASTM D256
Izod Impact, Unnotched	9.61 J/cm @Thickness 3.17 mm	18.0 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	36.0 Âµm/m-Â°C	20.0 Âµin/in-Â°F	ASTM D696
Deflection Temperature at 1.8 MPa (264 psi)	252 Â°C	485 Â°F	Unannealed; ASTM D648

Thermal Properties	V-0 Metric	V-0 English	Comments
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	5VB	5VB	
	@Thickness 2.00 mm	@Thickness 0.0787 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	ASTM D257
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	ASTM D257
Dielectric Strength	20.5 kV/mm	520 kV/in	Method A (Short-Time); ASTM D149
Comparative Tracking Index	>= 550 V	>= 550 V	UL 746

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China