

Techmer ES HiFill FR[®] PC FR RD064

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, Molded , Polycarbonate, Unreinforced, Flame Retardant

Material Notes:

Availability: North America Forms: Pellets Features: Flame Retardant UL File Number: E157318 Appearance: Red Processing Method: Injection Molding Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-FR-PC-FR-RD064.php

Physical Properties	Metric	English	Comments
Density	1.21 g/cc	0.0437 lb/in ³	ASTM D792
Water Absorption	0.15 % @Time 86400 sec	0.15 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0060 cm/cm @Thickness 3.17 mm	0.0060 in/in @Thickness 0.125 in	ASTM D955
Melt Flow	17 g/10 min @Load 1.20 kg, Temperature 300 Â°C	17 g/10 min @Load 2.65 lb, Temperature 572 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	118	118	ASTM D785
Tensile Strength	55.2 MPa	8000 psi	ASTM D638
Elongation at Yield	88 %	88 %	ASTM D638
Flexural Yield Strength	89.6 MPa	13000 psi	ASTM D790
Flexural Modulus	0.228 GPa	33.0 ksi	ASTM D790
Izod Impact, Notched	6.41 J/cm @Thickness 3.17 mm	12.0 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	68.4 Âµm/m-Â°C	38.0 Âµin/in-Â°F	ASTM D696
Deflection Temperature at 1.8 MPa (264 psi)	132 Â°C	270 Â°F	Unannealed; ASTM D648
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Electrical Properties	Metric	English	Comments
Surface Resistance	1.00e+16 ohm	1.00e+16 ohm	ASTM D257
Dielectric Strength	16.9 kV/mm	430 kV/in	Method A (Short-Time); ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China