

Techmer ES HiFill FR[®] PP CO FR-N V2

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer , Polypropylene, Flame Retardant , Polypropylene, Impact Modified; Molded/Extruded

Material Notes:

Availability: North America Forms: Pellets Features: Flame Retardant, High Impact Resistance and Copolymer Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-FR-PP-CO-FR-N-V2.php

Physical Properties	Metric	English	Comments
Density	0.950 g/cc	0.0343 lb/in ³	ASTM D792
Linear Mold Shrinkage, Flow	0.010 cm/cm @Thickness 3.17 mm	0.010 in/in @Thickness 0.125 in	ASTM D955
Melt Flow	20 g/10 min	20 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	17.2 MPa	2500 psi	ASTM D638
Elongation at Yield	110 %	110 %	ASTM D638
Flexural Yield Strength	22.8 MPa	3300 psi	ASTM D790
Flexural Modulus	0.621 GPa	90.0 ksi	ASTM D790
Izod Impact, Notched	3.20 J/cm @Thickness 3.17 mm	6.00 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	86.7 Å°C	188 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	51.7 Å°C	125 Å°F	Unannealed; ASTM D648
Flammability, UL94	V-2	V-2	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	ASTM D257
Dielectric Strength	17.7 kV/mm	450 kV/in	Method A (Short-Time); ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China