

Techmer ES HiFill FR® PPO/HIPS MM20 FR 20% Mineral Filled

Category : Polymer , Thermoplastic , Polyphenylene Ether/PPO , Polystyrene (PS) , Polystyrene + Polyphenylene Ether, Glass + Mineral Filler

Material Notes:

Availability: North America Forms: Pellets Filler/Reinforcement: Mineral Filler, 20% Filler by Weight Features: Flame Retardant Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-FR-PPOHIPS-MM20-FR-20-Mineral-Filled.php

Physical Properties	Metric	English	Comments
Density	1.24 g/cc	0.0448 lb/in ³	ASTM D792
Water Absorption	0.060 % @Time 86400 sec	0.060 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0060 cm/cm @Thickness 3.17 mm	0.0060 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	106	106	ASTM D785
Tensile Strength, Yield	75.8 MPa	11000 psi	ASTM D638
Elongation at Break	20 %	20 %	ASTM D638
Flexural Yield Strength	117 MPa	17000 psi	ASTM D790
Flexural Modulus	3.52 GPa	510 ksi	ASTM D790
Izod Impact, Notched	1.28 J/cm @Thickness 3.17 mm	2.40 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	36.0 µm/m-°C	20.0 µin/in-°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	126 °C	259 °F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	116 °C	240 °F	Unannealed; ASTM D648
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+17 ohm-cm	1.00e+17 ohm-cm	ASTM D257

Electrical Properties	Metric//mm	EnglishIn	CommentsShort-Time); ASTM D149
-----------------------	------------	-----------	--------------------------------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China