

Techmer ES HiFill® HDPE GF30 CC 30% Glass Filled

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Glass fiber Filled

Material Notes:

Availability: North America Forms: Pellets Filler/Reinforcement: Glass Fiber Reinforcement, 30% Filler by Weight Features: Chemically Coupled Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-HDPE-GF30-CC-30-Glass-Filled.php

Physical Properties	Metric	English	Comments
Density	1.17 g/cc	0.0423 lb/in ³	ASTM D792
Water Absorption	0.030 % @Time 86400 sec	0.030 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0030 cm/cm @Thickness 3.17 mm	0.0030 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	76	76	ASTM D785
Tensile Strength, Yield	58.6 MPa	8500 psi	ASTM D638
Elongation at Break	5.0 %	5.0 %	ASTM D638
Flexural Strength	75.8 MPa	11000 psi	ASTM D790
Flexural Modulus	4.14 GPa	600 ksi	ASTM D790
Izod Impact, Notched	1.66 J/cm @Thickness 3.17 mm	3.10 ft-lb/in @Thickness 0.125 in	ASTM D256
Izod Impact, Unnotched	6.94 J/cm @Thickness 3.17 mm	13.0 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	54.0 Åµm/m-Å°C	30.0 Åµin/in-Å°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	129 Å°C	265 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	121 Å°C	250 Å°F	Unannealed; ASTM D648
Flammability, UL94	HB	HB	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China