

Techmer ES HiFill® PA6 0365 01 BK

Category : Polymer , Thermoplastic , Nylon , Nylon 6

Material Notes:

Availability: North America Forms: Pellets Features: High Specific Gravity Appearance: Black Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-PA6-0365-01-BK.php

Physical Properties	Metric	English	Comments
Density	3.65 g/cc	0.132 lb/in ³	ASTM D792
Water Absorption	0.10 %	0.10 %	ASTM D570
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Flow	0.0040 cm/cm	0.0040 in/in	ASTM D955
	@Thickness 3.17 mm	@Thickness 0.125 in	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	44.8 MPa	6500 psi	ASTM D638
Elongation at Break	1.0 %	1.0 %	ASTM D638
Flexural Strength	48.3 MPa	7000 psi	ASTM D790
Flexural Modulus	6.89 GPa	1000 ksi	ASTM D790
Izod Impact, Notched	0.374 J/cm	0.700 ft-lb/in	ASTM D256
	@Thickness 3.17 mm	@Thickness 0.125 in	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	21.6 Åµm/m-Å°C	12.0 Åµin/in-Å°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	174 Å°C	345 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	167 Å°C	333 Å°F	Unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.0 - 100 ohm-cm	1.0 - 100 ohm-cm	ASTM D257

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China