

Techmer ES HiFill® PA6 1020

Category : Polymer , Thermoplastic , Nylon , Nylon 6

Material Notes:

Availability: North America Forms: Pellets Filler/Reinforcement: Unspecified Filler/Reinfor Features: High Specific Gravity Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-PA6-1020.php

Physical Properties	Metric	English	Comments
Density	10.2 g/cc	0.368 lb/in ³	ASTM D792
Water Absorption	0.10 % @Time 86400 sec	0.10 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0010 cm/cm @Thickness 3.17 mm	0.0010 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	58.6 MPa	8500 psi	ASTM D638
Elongation at Break	1.0 %	1.0 %	ASTM D638
Flexural Strength	48.3 MPa	7000 psi	ASTM D790
Flexural Modulus	15.2 GPa	2200 ksi	ASTM D790
Izod Impact, Notched	1.01 J/cm @Thickness 3.17 mm	1.90 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	124 Â°C	255 Â°F	Unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.0 - 100 ohm-cm	1.0 - 100 ohm-cm	ASTM D257

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China