

Techmer ES HiFill® PA6 GF10 TL10 BK 10% Glass Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 10% Glass Fiber Filled , Nylon 6, Heat Stabilized , Nylon 6, PTFE Filled

Material Notes:

Availability: North America Forms: Pellets Filler/Reinforcement: Glass Fiber Reinforcement, 10% Filler by Weight Additive: Heat Stabilizer and PTFE Lubricant Features: Heat Stabilized and Lubricated Appearance: Black Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-PA6-GF10-TL10-BK-10-Glass-Filled.php

Physical Properties	Metric	English	Comments
Density	1.33 g/cc	0.0480 lb/in ³	ASTM D792
Water Absorption	1.1 % @Time 86400 sec	1.1 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0060 cm/cm @Thickness 3.17 mm	0.0060 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	117	117	ASTM D785
Tensile Strength, Yield	75.8 MPa	11000 psi	ASTM D638
Elongation at Break	3.5 %	3.5 %	ASTM D638
Flexural Strength	103 MPa	15000 psi	ASTM D790
Flexural Modulus	3.59 GPa	520 ksi	ASTM D790
Izod Impact, Notched	0.641 J/cm @Thickness 3.17 mm	1.20 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	54.0 Åµm/m-Å°C	30.0 Åµin/in-Å°F	ASTM D696
Deflection Temperature at 1.8 MPa (264 psi)	204 Å°C	400 Å°F	Unannealed; ASTM D648
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Volume Resistivity	3.00e+14 ohm-cm	3.00e+14 ohm-cm	ASTM D257
Dielectric Strength	16.5 kV/mm	420 kV/in	Method A (Short-Time); ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China