

Techmer ES HiFill® PA6 GF20 L BK001 20% Glass Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, 20% Glass Fiber Filled

Material Notes:

Availability: North America Forms: Pellets Filler/Reinforcement: Glass Fiber Reinforcement, 20% Filler by Weight Additive:

Lubricant Features: Lubricated Appearance: Black TPCI# 8376102 Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-PA6-GF20-L-BK001-20-Glass-Filled.php

Physical Properties	Metric	English	Comments
Density	1.30 g/cc	0.0470 lb/in ³	ASTM D792
Water Absorption	1.4 % @Time 86400 sec	1.4 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0040 cm/cm @Thickness 3.17 mm	0.0040 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	115	115	ASTM D785
Tensile Strength, Yield	131 MPa	19000 psi	ASTM D638
Elongation at Break	3.5 %	3.5 %	ASTM D638
Flexural Strength	200 MPa	29000 psi	ASTM D790
Flexural Modulus	6.89 GPa	1000 ksi	ASTM D790
Izod Impact, Notched	0.747 J/cm @Thickness 3.17 mm	1.40 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	19.8 Åµm/m-Å°C	11.0 Åµin/in-Å°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	213 Å°C	415 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	204 Å°C	400 Å°F	Unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	ASTM D257
Dielectric Strength	15.7 kV/mm	400 kV/in	Method A (Short-Time); ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China