

Techmer ES HiFill® PA6 GF50 IM L NAT001 50% Glass Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 50% Glass Fiber Filled , Nylon 6, Impact Grade

Material Notes:

Availability: North America
Forms: Pellets
Filler/Reinforcement: Glass Fiber Reinforcement, 50% Filler by Weight
Additive: Lubricant and Impact Modifier
Features: Lubricated and Impact Modified
Processing Method: Injection Molding
Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-PA6-GF50-IM-L-NAT001-50-Glass-Filled.php

Physical Properties	Metric	English	Comments
Density	1.57 g/cc	0.0567 lb/in ³	ASTM D792
Water Absorption	0.70 % @Time 86400 sec	0.70 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0022 cm/cm @Thickness 3.17 mm	0.0022 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	121	121	ASTM D785
Tensile Strength, Yield	200 MPa	29000 psi	ASTM D638
Elongation at Break	2.8 %	2.8 %	ASTM D638
Flexural Strength	310 MPa	45000 psi	ASTM D790
Flexural Modulus	11.4 GPa	1650 ksi	ASTM D790
Izod Impact, Notched	2.67 J/cm @Thickness 3.17 mm	5.00 ft-lb/in @Thickness 0.125 in	ASTM D256
Izod Impact, Unnotched	17.6 J/cm @Thickness 3.17 mm	33.0 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	14.4 Åµm/m-Å°C	8.00 Åµin/in-Å°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	218 Å°C	425 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	213 Å°C	415 Å°F	Unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	ASTM D257
Dielectric Strength	17.7 kV/mm	450 kV/in	Method A (Short-Time); ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China