

Techmer ES HiFill® PA6/6 GF50 HS L BK 50% Glass Filled (Dry)

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 50% Glass Fiber Filled , Nylon 66, Heat Stabilized

Material Notes:

Availability: North America Forms: Pellets Filler/Reinforcement: Glass Fiber Reinforcement, 50% Filler by Weight Additive: Lubricant and Heat Stabilizer Features: Lubricated and Heat Stabilized Appearance: Black Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-PA66-GF50-HS-L-BK-50-Glass-Filled-Dry.php

Physical Properties	Metric	English	Comments
Density	1.57 g/cc	0.0567 lb/in ³	ASTM D792
Water Absorption	0.45 % @Time 86400 sec	0.45 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0030 cm/cm @Thickness 3.17 mm	0.0030 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	121	121	ASTM D785
Tensile Strength, Yield	228 MPa	33000 psi	ASTM D638
Elongation at Break	2.5 %	2.5 %	ASTM D638
Flexural Strength	331 MPa	48000 psi	ASTM D790
Flexural Modulus	15.9 GPa	2300 ksi	ASTM D790
Izod Impact, Notched	1.44 J/cm @Thickness 3.17 mm	2.70 ft-lb/in @Thickness 0.125 in	ASTM D256
Izod Impact, Unnotched	10.7 J/cm @Thickness 3.17 mm	20.0 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	16.2 Âµm/m-Â°C	9.00 Âµin/in-Â°F	ASTM D696
Melting Point	255 Â°C	491 Â°F	
Deflection Temperature at 0.46 MPa (66 psi)	260 Â°C	500 Â°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	260 Â°C	500 Â°F	Unannealed; ASTM D648

Flammability: UL 94 Thermal Properties	HB Metric	HB English	Comments
Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	ASTM D257
Dielectric Strength	18.9 kV/mm	480 kV/in	Method A (Short-Time); ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China