

Techmer ES HiFill® POM CO 0241 S Acetal

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Copolymer, Steel Filled

Material Notes:

Availability: North AmericaForms: PelletsFiller/Reinforcement: MetalFeatures: CopolymerInformation provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-POM-CO-0241-S-Acetal.php

Physical Properties	Metric	English	Comments
Density	2.41 g/cc	0.0871 lb/in ³	ASTM D792
Water Absorption	0.20 %	0.20 %	ASTM D570
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Flow	0.016 cm/cm	0.016 in/in	ASTM D955
	@Thickness 3.17 mm	@Thickness 0.125 in	
Melt Flow	7.0 g/10 min	7.0 g/10 min	ASTM D1238
	@Load 2.16 kg, Temperature 190 °C	@Load 4.76 lb, Temperature 374 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	100	100	ASTM D785
Tensile Strength, Yield	48.3 MPa	7000 psi	ASTM D638
Elongation at Break	40 %	40 %	ASTM D638
Flexural Strength	79.3 MPa	11500 psi	ASTM D790
Flexural Modulus	3.24 GPa	470 ksi	ASTM D790
Izod Impact, Notched	0.587 J/cm	1.10 ft-lb/in	ASTM D256
	@Thickness 3.17 mm	@Thickness 0.125 in	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	21.6 µm/m-°C	12.0 µin/in-°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	160 °C	320 °F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	110 °C	230 °F	Unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Volume Resistivity	1.00e+14 ohm-cm	1.00e+14 ohm-cm	ASTM D257
Electrical Properties	Metric	English	Comments

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China