

Techmer ES HiFill® PP GF20 CC HS 20% Glass Filled

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 20% Glass Fiber Filler

Material Notes:

Availability: North America Forms: Pellets Filler/Reinforcement: Glass Fiber Reinforcement, 20% Filler by Weight Additive: Heat Stabilizer Features: Heat Stabilized and Chemically Coupled Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-PP-GF20-CC-HS-20-Glass-Filled.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in ³	ASTM D792
Water Absorption	0.010 % @Time 86400 sec	0.010 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0040 cm/cm @Thickness 3.17 mm	0.0040 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	112	112	ASTM D785
Tensile Strength, Yield	77.9 MPa	11300 psi	ASTM D638
Elongation at Yield	4.7 %	4.7 %	ASTM D638
Flexural Yield Strength	97.2 MPa	14100 psi	ASTM D790
Flexural Modulus	4.14 GPa	600 ksi	ASTM D790
Izod Impact, Notched	0.961 J/cm @Thickness 3.17 mm	1.80 ft-lb/in @Thickness 0.125 in	ASTM D256
Izod Impact, Unnotched	5.87 J/cm @Thickness 3.17 mm	11.0 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	45.0 Åµm/m-Å°C	25.0 Åµin/in-Å°F	ASTM D696
Melting Point	163 Å°C	325 Å°F	
Deflection Temperature at 0.46 MPa (66 psi)	160 Å°C	320 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	152 Å°C	305 Å°F	Unannealed; ASTM D648

Flammability: UL 94 Thermal Properties	HB Metric	HB English	Comments
Electrical Properties	Metric	English	Comments
Volume Resistivity	4.00e+16 ohm-cm	4.00e+16 ohm-cm	ASTM D257
Dielectric Strength	20.9 kV/mm	530 kV/in	Method A (Short-Time); ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China