

Techmer ES Luriblend® PA6 GF40 ML5 HS 12 mm 40% Glass Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, 40% Glass Fiber Filled , Nylon 6, Heat Stabilized

Material Notes:

Availability: North America Forms: Pellets Filler/Reinforcement: Glass Fiber, 40% Filler by Weight Additive: Heat Stabilized and Molybdenum Disulfide Lubricant Features: Lubricated and Heat Stabilizer Appearance: Black Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-Luriblend-PA6-GF40-ML5-HS-12-mm-40-Glass-Filled.php

Physical Properties	Metric	English	Comments
Density	1.46 g/cc	0.0527 lb/in ³	ASTM D792
Water Absorption	0.80 % @Time 86400 sec	0.80 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0030 cm/cm @Thickness 3.17 mm	0.0030 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	122	122	ASTM D785
Tensile Strength, Yield	200 MPa	29000 psi	ASTM D638
Elongation at Break	3.0 %	3.0 %	ASTM D638
Flexural Strength	269 MPa	39000 psi	ASTM D790
Flexural Modulus	10.3 GPa	1500 ksi	ASTM D790
Izod Impact, Notched	1.44 J/cm @Thickness 3.17 mm	2.70 ft-lb/in @Thickness 0.125 in	ASTM D256
Izod Impact, Unnotched	7.47 J/cm @Thickness 3.17 mm	14.0 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	27.0 Åµm/m-Å°C	15.0 Åµin/in-Å°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	218 Å°C	425 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	216 Å°C	420 Å°F	Unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Volume Resistivity Electrical Properties	1.00e+14 ohm-cm Metric	1.00e+14 ohm-cm English	ASTM D257 Comments
Dielectric Strength	17.7 kV/mm	450 kV/in	Method A (Short-Time); ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China