

Techmer ES Luriblend® PA6 TL25 Nylon 6

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, Heat Stabilized , Nylon 6, PTFE Filled

Material Notes:

Availability: North America Forms: Pellets Additive: Heat Stabilizer and PTFE Lubricant (25%) Features: Heat Stabilized and Lubricated Appearance: Black Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-Luriblend-PA6-TL25-Nylon-6.php

Physical Properties	Metric	English	Comments
Density	1.31 g/cc	0.0473 lb/in ³	ASTM D792
Water Absorption	1.0 % @Time 86400 sec	1.0 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.017 cm/cm @Thickness 3.17 mm	0.017 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	116	116	ASTM D785
Tensile Strength, Yield	55.8 MPa	8100 psi	ASTM D638
Elongation at Break	9.5 %	9.5 %	ASTM D638
Flexural Strength	82.7 MPa	12000 psi	ASTM D790
Flexural Modulus	2.14 GPa	310 ksi	ASTM D790
Izod Impact, Notched	0.534 J/cm @Thickness 3.17 mm	1.00 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	84.6 Åµm/m-Å°C	47.0 Åµin/in-Å°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	135 Å°C	275 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	79.4 Å°C	175 Å°F	Unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+14 ohm-cm	1.00e+14 ohm-cm	ASTM D257
Dielectric Strength	15.7 kV/mm	400 kV/in	Method A (Short-Time); ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China