

Techmer ES Luriblend® PA6/6 CF20 TS15 BK 20% Carbon Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Carbon Fiber/PTFE Filled

Material Notes:

Availability: North America
Forms: Pellets
Filler/Reinforcement: Carbon Fiber, 20% Filler by Weight
Additive: PTFE Lubricant(10%) and Silicone Lubricant
Features: Lubricated, Good Wear Resistance and Low Friction
Appearance: Black
Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-Luriblend-PA66-CF20-TS15-BK-20-Carbon-Filled.php

Physical Properties	Metric	English	Comments
Density	1.27 g/cc	0.0459 lb/in ³	ASTM D792
Water Absorption	0.45 % @Time 86400 sec	0.45 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0040 cm/cm @Thickness 3.17 mm	0.0040 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	120	120	ASTM D785
Tensile Strength, Yield	186 MPa	27000 psi	ASTM D638
Elongation at Break	2.5 %	2.5 %	ASTM D638
Flexural Strength	262 MPa	38000 psi	ASTM D790
Flexural Modulus	12.8 GPa	1850 ksi	ASTM D790
Izod Impact, Notched	0.747 J/cm @Thickness 3.17 mm	1.40 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	254 Â°C	490 Â°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	252 Â°C	485 Â°F	Unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Volume Resistivity	10 - 1000 ohm-cm	10 - 1000 ohm-cm	ASTM D257

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China