

Techmer ES Luriblend® PA6/6 GF30 ML5 HS 30% Glass Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Glass Fiber Filled , Nylon 66, Heat Stabilized

Material Notes:

Availability: North America Forms: Pellets Filler/Reinforcement: Glass Fiber, 30% Filler by Weight Additive: Heat Stabilizer and Molybdenum Disulfide Lubricant(5%) Features: Lubricated and Heat Stabilized Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-Luriblend-PA66-GF30-ML5-HS-30-Glass-Filled.php

Physical Properties	Metric	English	Comments
Density	1.43 g/cc	0.0517 lb/in ³	ASTM D792
Water Absorption	0.70 % @Time 86400 sec	0.70 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0040 cm/cm @Thickness 3.17 mm	0.0040 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	138 MPa	20000 psi	ASTM D638
Elongation at Break	4.5 %	4.5 %	ASTM D638
Flexural Strength	203 MPa	29500 psi	ASTM D790
Flexural Modulus	9.31 GPa	1350 ksi	ASTM D790
Compressive Strength	110 MPa	16000 psi	ASTM D256
Izod Impact, Notched	1.01 J/cm @Thickness 3.17 mm	1.90 ft-lb/in @Thickness 0.125 in	ASTM D256
Izod Impact, Unnotched	10.1 J/cm @Thickness 3.17 mm	19.0 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	72.0 Åµm/m-Å°C	40.0 Åµin/in-Å°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	254 Å°C	490 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	246 Å°C	475 Å°F	Unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Volume Resistivity Electrical Properties	1.00e+14 ohm-cm Metric	1.00e+14 ohm-cm English	ASTM D257 Comments
Dielectric Strength	19.7 kV/mm	500 kV/in	Method A (Short-Time); ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China