

Techmer ES Luriblend® PA6/6 GF30 TL15 UV 30% Glass Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Glass Fiber Filled , Nylon 66, Heat Stabilized , Nylon 66, PTFE Filled

Material Notes:

Availability: North America
Forms: Pellets
Filler/Reinforcement: Glass Fiber, 30% Filler by Weight
Additive: Heat Stabilizer, UV Stabilizer and PTFE Lubricant(15%)
Features: Lubricated, Good Wear Resistance, Low Friction, Good UV Resistance and Heat Stabilized
Appearance: Natural Color
Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-Luriblend-PA66-GF30-TL15-UV-30-Glass-Filled.php

Physical Properties	Metric	English	Comments
Density	1.49 g/cc	0.0538 lb/in ³	ASTM D792
Water Absorption	0.50 % @Time 86400 sec	0.50 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0050 cm/cm @Thickness 3.17 mm	0.0050 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	90	90	ASTM D785
Tensile Strength, Yield	149 MPa	21600 psi	ASTM D638
Elongation at Break	2.0 %	2.0 %	ASTM D638
Flexural Strength	224 MPa	32500 psi	ASTM D790
Flexural Modulus	8.96 GPa	1300 ksi	ASTM D790
Izod Impact, Notched	0.747 J/cm @Thickness 3.17 mm	1.40 ft-lb/in @Thickness 0.125 in	ASTM D256
Coefficient of Friction, Dynamic	0.28	0.28	ASTM D1894
Coefficient of Friction, Static	0.22	0.22	ASTM D1894
K (wear) Factor	36.3 x 10 ⁻⁸ mm ³ /N-M	18.0 x 10 ⁻¹⁰ in ³ -min/ft-lb-hr	
Limiting Pressure Velocity	0.613 MPa-m/sec	17500 psi-ft/min	10 fpm
	0.613 MPa-m/sec	17500 psi-ft/min	1000 fpm
	0.701 MPa-m/sec	20000 psi-ft/min	100 fpm

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	27.0 $\mu\text{m/m}\cdot^\circ\text{C}$	15.0 $\mu\text{in/in}\cdot^\circ\text{F}$	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	259 $^\circ\text{C}$	498 $^\circ\text{F}$	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	254 $^\circ\text{C}$	490 $^\circ\text{F}$	Unannealed; ASTM D648
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+14 ohm-cm	1.00e+14 ohm-cm	ASTM D257
Dielectric Strength	19.7 kV/mm	500 kV/in	Method A (Short-Time); ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China