

Techmer ES Luriblend® POM HO TL2 Acetal

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Homopolymer, PTFE-Filled

Material Notes:

Availability: North America Forms: Pellets Additive: PTFE Lubricant(2%) Features: Lubricated, Good Wear Resistance and Homopolymer Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-Luriblend-POM-HO-TL2-Acetal.php

Physical Properties	Metric	English	Comments
Density	1.42 g/cc	0.0513 lb/in ³	ASTM D792
Water Absorption	0.17 % @Time 86400 sec	0.17 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.020 cm/cm @Thickness 3.17 mm	0.020 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	92	92	ASTM D785
Tensile Strength	60.7 MPa	8800 psi	ASTM D638
Elongation at Yield	22 %	22 %	ASTM D638
Flexural Yield Strength	89.6 MPa	13000 psi	ASTM D790
Flexural Modulus	2.96 GPa	430 ksi	ASTM D790
Izod Impact, Notched	0.534 J/cm @Thickness 3.17 mm	1.00 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	90.0 Åµm/m-Å°C	50.0 Åµin/in-Å°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	166 Å°C	330 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	100 Å°C	212 Å°F	Unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	ASTM D257
Dielectric Strength	17.7 kV/mm	450 kV/in	Method A (Short-Time); ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China