

Techmer ES Plaslube® J-1/30/TF/15 BK223 PA66

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Glass Fiber Filled

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-Plaslube-J-130TF15-BK223-PA66.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.52 g/cc	1.52 g/cc	ASTM D792
Water Absorption	0.60 %	0.60 %	24 Hrs; ASTM D570
Linear Mold Shrinkage	0.0020 cm/cm	0.0020 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	119	119	ASTM D785
Tensile Strength at Break	159 MPa	23000 psi	ASTM D638
Elongation at Break	2.5 %	2.5 %	ASTM D638
Flexural Strength	238 MPa	34500 psi	ASTM D790
Flexural Modulus	9.31 GPa	1350 ksi	ASTM D790
Izod Impact, Notched	1.33 J/cm	2.50 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	43.2 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$ @Temperature 20.0 $\text{Å}^\circ\text{C}$	24.0 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$ @Temperature 68.0 $\text{Å}^\circ\text{F}$	ASTM D696
Deflection Temperature at 1.8 MPa (264 psi)	254 $\text{Å}^\circ\text{C}$	490 $\text{Å}^\circ\text{F}$	ASTM D648
Flammability, UL94	HB @Thickness 1.59 mm	HB @Thickness 0.0625 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China