

Techmer ES Plaslube® J-3/30/TF/13/SI/2 Nylon 6, 30% GFR, 13% PTFE, 2% Silicone

Category: Polymer, Thermoplastic, Nylon, Nylon 6, Nylon 6, Glass Fiber/Solid Lube Filled

Material Notes:

Plaslube glass fiber reinforced polytetrafluoroethylene (PTFE) lubricated nylon 612 grades offer a unique balance of excellent wear and friction performance with good dimensional stability and mechanical strength. These characteristics are typical of gear train, pulley, and other bearing applications. Further wear and friction performance can be achieved by utilizing both PTFE and silicone. For less dimensionally critical applications, our nylon 6 grades offer similar performance characteristics.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-Plaslube-J-330TF13SI2-Nylon-6-30-GFR-13-PTFE-2-Silicone.php

| Physical Properties | Metric | English | Comments |
|-----------------------|--------------------|---------------------|-------------------|
| Density | 1.48 g/cc | 0.0535 lb/in³ | ASTM D792 |
| Water Absorption | 0.75 % | 0.75 % | 24 hrs. ASTM D570 |
| Linear Mold Shrinkage | 0.0030 cm/cm | 0.0030 in/in | ASTM D955 |
| | @Thickness 3.17 mm | @Thickness 0.125 in | |

| Mechanical Properties | Metric | English | Comments |
|----------------------------------|--------------------------------|---|---|
| Tensile Strength, Ultimate | 165 MPa | 24000 psi | ASTM D638 |
| Flexural Yield Strength | 228 MPa | 33000 psi | ASTM D790 |
| Flexural Modulus | 9.31 GPa | 1350 ksi | ASTM D790 |
| Izod Impact, Notched | 1.39 J/cm | 2.60 ft-lb/in | ASTM D256 |
| | @Thickness 3.17 mm | @Thickness 0.125 in | |
| Coefficient of Friction, Dynamic | 0.20 | 0.20 | |
| Coefficient of Friction, Static | 0.17 | 0.17 | |
| K (wear) Factor | 121 x 10 ⁻⁸ mm³/N-M | 60.0 x 10 ⁻¹⁰ in³- min/ft-lb-hr | Thrust washer at 2000 PV |
| Limiting Pressure Velocity | 0.560 MPa-m/sec | 16000 psi-ft/min | at 100 FPM, ambient temperature, thrust washer. |

| Thermal Properties | Metric | English | Comments |
|--|--------|---------|-----------|
| Deflection Temperature at 1.8 MPa (264 psi) | 213 °C | 415 °F | ASTM D648 |

Contact Songhan Plastic Technology Co.,Ltd.



Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China