

Techmer ES Plaslube® PC-50/TF/13/SI/2 BK3585 Polycarbonate

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, PTFE Filled

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-Plaslube-PC-50TF13SI2-BK3585-Polycarbonate.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.27 g/cc	1.27 g/cc	ASTM D792
Water Absorption	0.12 %	0.12 %	24 Hrs; ASTM D570
Linear Mold Shrinkage	0.0070 cm/cm	0.0070 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	109	109	ASTM D785
Tensile Strength at Break	48.3 MPa	7000 psi	ASTM D638
Flexural Strength	72.4 MPa	10500 psi	ASTM D790
Flexural Modulus	2.00 GPa	290 ksi	ASTM D790
Compressive Strength	62.1 MPa	9000 psi	ASTM D695
Izod Impact, Notched	2.14 J/cm	4.00 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	68.4 $\mu\text{m/m-}^{\circ}\text{C}$ @Temperature 20.0 $^{\circ}\text{C}$	38.0 $\mu\text{in/in-}^{\circ}\text{F}$ @Temperature 68.0 $^{\circ}\text{F}$	ASTM D696
Deflection Temperature at 1.8 MPa (264 psi)	136 $^{\circ}\text{C}$	276 $^{\circ}\text{F}$	ASTM D648
Flammability, UL94	HB @Thickness 1.59 mm	HB @Thickness 0.0625 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China