

Techmer ES Plastiblend® LDPE E FR V-2

Category : Polymer , Thermoplastic , Polyethylene (PE) , LDPE

Material Notes:

Availability: North America Forms: Pellets Features: Flame Retardant Processing Method: Extrusion Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-Plastiblend-LDPE-E-FR-V-2.php

Physical Properties	Metric	English	Comments
Density	1.17 g/cc	0.0423 lb/in ³	ASTM D792
Water Absorption	0.020 % @Time 86400 sec	0.020 % @Time 24.0 hour	ASTM D570
Melt Flow	1.0 g/10 min @Load 2.16 kg, Temperature 190 °C	1.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	20.0 MPa	2900 psi	ASTM D638
Elongation at Break	200 %	200 %	ASTM D638
Flexural Strength	28.3 MPa	4100 psi	ASTM D790
Flexural Modulus	0.827 GPa	120 ksi	ASTM D790
Izod Impact, Notched	0.534 J/cm @Thickness 3.17 mm	1.00 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Flammability, UL94	V-1 @Thickness 1.50 mm	V-1 @Thickness 0.0591 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China

