

Techmer ES Plastiblend® PC/ABS 1950

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Unreinforced , Polycarbonate (PC)

Material Notes:

Availability: North America Forms: Pellets Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-Plastiblend-PCABS-1950.php

Physical Properties	Metric	English	Comments
Density	1.12 g/cc	0.0405 lb/in ³	ASTM D792
Water Absorption	0.10 % @Time 86400 sec	0.10 % @Time 24.0 hour	ASTM D570
Melt Flow	3.0 g/10 min @Load 3.80 kg, Temperature 230 °C	3.0 g/10 min @Load 8.38 lb, Temperature 446 °F	ASTM D1238
	7.0 g/10 min @Load 5.00 kg, Temperature 260 °C	7.0 g/10 min @Load 11.0 lb, Temperature 500 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	115	115	ASTM D785
Tensile Strength, Yield	57.9 MPa	8400 psi	ASTM D638
Elongation at Break	80 %	80 %	ASTM D638
Flexural Yield Strength	91.0 MPa	13200 psi	ASTM D790
Flexural Modulus	2.48 GPa	360 ksi	ASTM D790
Izod Impact, Notched	8.01 J/cm @Thickness 3.17 mm	15.0 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	72.0 µm/m-°C	40.0 µin/in-°F	ASTM D696
Deflection Temperature at 1.8 MPa (264 psi)	98.9 °C	210 °F	Unannealed; ASTM D648
Flammability, UL94	HB	HB	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China