

Techmer ES Plastiblend® PC/PBT IM 6600

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate/Polybutylene Terephthalate (PBT) Blend, Unreinforced , Polyester, TP , Polybutylene Terephthalate (PBT)

Material Notes:

Availability: North America Forms: Pellets Additive: Impact Modifier Features: Impact Modified Appearance: Black Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-Plastiblend-PCPBT-IM-6600.php

Physical Properties	Metric	English	Comments
Density	1.18 g/cc	0.0426 lb/in ³	ASTM D792
Water Absorption	0.10 % @Time 86400 sec	0.10 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0080 cm/cm @Thickness 3.17 mm	0.0080 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	40.0 MPa	5800 psi	ASTM D638
Elongation at Break	120 %	120 %	ASTM D638
Flexural Yield Strength	84.1 MPa	12200 psi	ASTM D790
Flexural Modulus	1.86 GPa	270 ksi	ASTM D790
Izod Impact, Notched	7.47 J/cm @Thickness 3.17 mm, Temperature -40.0 Â°C	14.0 ft-lb/in @Thickness 0.125 in, Temperature -40.0 Â°F	ASTM D256
	7.47 J/cm @Thickness 3.17 mm, Temperature 22.8 Â°C	14.0 ft-lb/in @Thickness 0.125 in, Temperature 73.0 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	82.8 Âµm/m-Â°C	46.0 Âµin/in-Â°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	118 Â°C	245 Â°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	98.9 Â°C	210 Â°F	Unannealed; ASTM D648
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	ASTM D257

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China