

Techmer ES Plastiblend® TPX-HTN-000AA

Category : Polymer , Thermoplastic , Nylon , High Temperature Nylon

Material Notes:

Availability: North America Forms: Pellets Features: High Heat Resistance Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-Plastiblend-TPX-HTN-000AA.php

Physical Properties	Metric	English	Comments
Density	1.18 g/cc	0.0426 lb/in ³	ASTM D792
Water Absorption	2.3 % @Time 86400 sec	2.3 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0019 cm/cm @Thickness 3.17 mm	0.0019 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	120	120	ASTM D785
Tensile Strength, Yield	77.9 MPa	11300 psi	ASTM D638
Elongation at Break	30 %	30 %	ASTM D638
Flexural Strength	150 MPa	21700 psi	ASTM D790
Flexural Modulus	3.17 GPa	460 ksi	ASTM D790
Izod Impact, Notched	0.961 J/cm @Thickness 3.17 mm	1.80 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	73.8 Åµm/m-Å°C	41.0 Åµin/in-Å°F	ASTM D696
Melting Point	146 Å°C	295 Å°F	
Maximum Service Temperature, Inert	130 Å°C	266 Å°F	ASTM D794
Deflection Temperature at 1.8 MPa (264 psi)	160 Å°C	320 Å°F	Unannealed; ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China