

Teijin Multilon DN-1530B Filler Reinforced Type, Halogen-Free Flame Resistant PC/ABS Polymer Alloy

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate (PC)

Material Notes:

Halogen-free flame retardant PC/ABS polymer alloy, and is also antimony-free. It has improved stiffness through the addition of 30 % filler. Improved stiffness and high fluidity realizes a thin wall of OA machines etc. Applications: Thin wall components of mechanical, electric and electronic equipment that need least warpage and dimensional accuracy etc. Information provided by Teijin Chemicals Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Teijin-Multilon-DN-1530B-Filler-Reinforced-Type-Halogen-Free-Flame-Resistant-PCABS-Polymer-Alloy.php

Physical Properties	Metric	English	Comments
Density	1.40 g/cc	0.0506 lb/in ³	ISO 1183
Linear Mold Shrinkage	0.0010 - 0.0030 cm/cm	0.0010 - 0.0030 in/in	
	@Thickness 4.00 mm	@Thickness 0.157 in	
Linear Mold Shrinkage, Transverse	0.0020 - 0.0040 cm/cm	0.0020 - 0.0040 in/in	
	@Thickness 4.00 mm	@Thickness 0.157 in	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	65.0 MPa	9430 psi	50mm/min; ISO 527
Elongation at Break	2.0 %	2.0 %	50mm/min; ISO 527
Tensile Modulus	9.00 GPa	1310 ksi	1mm/min; ISO 527
Flexural Strength	110 MPa	16000 psi	2mm/min; ISO 178
Flexural Modulus	8.00 GPa	1160 ksi	2mm/min; ISO 178
Charpy Impact Unnotched	2.00 J/cm ²	9.52 ft-lb/in ²	ISO 179
Charpy Impact, Notched	0.400 J/cm ²	1.90 ft-lb/in ²	ISO 179

Thermal Properties	Metric	English	Comments
CTE, linear	30.0 Åµm/m-Å°C	16.7 Åµin/in-Å°F	ISO 11359
	@Temperature 20.0 Å°C	@Temperature 68.0 Å°F	
CTE, linear, Transverse to Flow	35.0 Åµm/m-Å°C	19.4 Åµin/in-Å°F	ISO 11359
	@Temperature 20.0 Å°C	@Temperature 68.0 Å°F	

Thermal Properties Deflection Temperature at 0.46 MPa (0.07 psi)	Metric 120 Â°C	English 248 Â°F	ISO 75 Comments
Deflection Temperature at 1.8 MPa (264 psi)	108 Â°C	226 Â°F	ISO 75
Vicat Softening Point	122 Â°C	252 Â°F	50Â°C/hr, 50N; ISO 306
Flammability, UL94	V-1	V-1	black
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	V-1	V-1	
	@Thickness 3.00 mm	@Thickness 0.118 in	
	5VB	5VB	
	@Thickness 2.00 mm	@Thickness 0.0787 in	

Electrical Properties	Metric	English	Comments
Surface Resistance	1.00e+16 ohm	1.00e+16 ohm	IEC 60093

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China