

Teijin Panlite® BS-8110R Friction and Abrasion Resistant, Carbon Fiber Reinforced Polycarbonate Resin

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, Carbon Fiber Reinforced

Material Notes:

CF 10% reinforced grade, meeting UL 94 V-2. it is compounded with fluorine powder to improve friction and abrasion resistance and also exhibits a mold release property, maintaining excellent characteristics of polycarbonate resin. Applications: Mechanical, electric and electronic components that need abrasion and friction resistance. Information provided by Teijin Chemicals Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Teijin-Panlite-BS-8110R-Friction-and-Abrasion-Resistant-Carbon-Fiber-Reinforced-Polycarbonate-Resin.php

Physical Properties	Metric	English	Comments
Density	1.29 g/cc	0.0466 lb/in ³	ISO 1183
Water Absorption	0.16 %	0.16 %	in water, 23°C, 24h; ISO 62
Linear Mold Shrinkage	0.0010 - 0.0030 cm/cm @Thickness 4.00 mm	0.0010 - 0.0030 in/in @Thickness 0.157 in	
Linear Mold Shrinkage, Transverse	0.0040 - 0.0060 cm/cm @Thickness 4.00 mm	0.0040 - 0.0060 in/in @Thickness 0.157 in	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	110 MPa	16000 psi	50mm/min; ISO 527
Elongation at Break	2.0 %	2.0 %	50mm/min; ISO 527
Tensile Modulus	7.80 GPa	1130 ksi	1mm/min; ISO 527
Flexural Strength	160 MPa	23200 psi	2mm/min; ISO 178
Flexural Modulus	7.50 GPa	1090 ksi	2mm/min; ISO 178
Charpy Impact Unnotched	2.70 J/cm ²	12.8 ft-lb/in ²	ISO 179
Charpy Impact, Notched	0.800 J/cm ²	3.81 ft-lb/in ²	ISO 179

Thermal Properties	Metric	English	Comments
CTE, linear	30.0 µm/m-°C @Temperature 20.0 °C	16.7 µin/in-°F @Temperature 68.0 °F	ISO 11359
CTE, linear, Transverse to Flow	60.0 µm/m-°C @Temperature 20.0 °C	33.3 µin/in-°F @Temperature 68.0 °F	ISO 11359

Thermal Properties (ISO 75)	Metric 150 °C	English 297 °F	Comments ISO 75
Deflection Temperature at 0.46 MPa (264 psi)	147 °C	297 °F	ISO 75
Vicat Softening Point	152 °C	306 °F	50°C/hr, 50N; ISO 306
UL RTI, Electrical	80.0 °C @Thickness 1.47 mm	176 °F @Thickness 0.0579 in	UL 746B
UL RTI, Mechanical with Impact	80.0 °C @Thickness 1.47 mm	176 °F @Thickness 0.0579 in	UL 746B
UL RTI, Mechanical without Impact	80.0 °C @Thickness 1.47 mm	176 °F @Thickness 0.0579 in	UL 746B
Flammability, UL94	V-2 @Thickness 0.750 mm	V-2 @Thickness 0.0295 in	
	V-1 @Thickness 1.50 mm	V-1 @Thickness 0.0591 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.0 - 100 ohm-cm	1.0 - 100 ohm-cm	IEC 60093
Surface Resistance	10 - 1000 ohm	10 - 1000 ohm	IEC 60093

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China