

Teknor Apex APEX[®] 4103 Polyvinyl Chloride, Flexible

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Flexible Grade , PVC, Wire and Cable Grade

Material Notes:

Notes: 60[°]C General Purpose; RoHS Compliant Uses: Connectors; Grommets; Plugs; Strain Reliefs
 Forms: Pellets Processing Method: Injection Molding Agency Ratings: UL QMFZ2 .E54709 Wire Types: Molded Components Additional Information: Temperature Rating: 60[°]C
 Recognized Component, CSA C22.2 No. 0.6, CSA Flammability Classification: 0.6HB at 0.86mm Information Provided by Teknor Apex

Order this product through the following link:

http://www.lookpolymers.com/polymer_Teknor-Apex-APEX-4103-Polyvinyl-Chloride-Flexible.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.38 g/cc	1.38 g/cc	ASTM D792
Linear Mold Shrinkage	0.010 - 0.012 cm/cm	0.010 - 0.012 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	80	80	15 seconds; ASTM D2240
Tensile Strength at Break	10.3 MPa	1500 psi	ASTM D638
Elongation at Break	220 %	220 %	ASTM D638

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	60.0 [°] C	140 [°] F	Continuous Use; ASTM D794
Brittleness Temperature	-26.0 [°] C	-14.8 [°] F	ASTM D746
UL RTI, Electrical	90.0 [°] C	194 [°] F	UL 746
	@Thickness 0.810 mm	@Thickness 0.0319 in	
UL RTI, Mechanical without Impact	90.0 [°] C	194 [°] F	UL 746
	@Thickness 3.00 mm	@Thickness 0.118 in	
Flammability, UL94	90.0 [°] C	194 [°] F	UL 746
	@Thickness 0.810 mm	@Thickness 0.0319 in	
Flammability, UL94	V-2	V-2	UL 746
	@Thickness 3.00 mm	@Thickness 0.118 in	

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Electrical Properties	Metric	English	Comments
Comparative Tracking Index	>= 600 V @Thickness 3.00 mm	>= 600 V @Thickness 0.118 in	UL 746
Hot Wire Ignition, HWI	60 - 120 sec @Thickness 3.00 mm	60 - 120 sec @Thickness 0.118 in	UL 746
High Amp Arc Ignition, HAI	60 - 120 arcs @Thickness 3.00 mm	60 - 120 arcs @Thickness 0.118 in	UL 746

Processing Properties	Metric	English	Comments
Melt Temperature	179 Â°C	355 Â°F	Processing Temperature

Descriptive Properties	Value	Comments
Appearance	Opaque	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China