

Teknor Apex Flexalloy® 9300-70 Polyvinyl Chloride Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE , Vinyl (PVC)

Material Notes:

Material Status-Commercial: ActiveAvailability-North AmericaTest Standards Available-ASTM Features: Good Flexibility, Oil Resistant, Ultra High MW, Recyclable, Good Thermal Stability, Good Weather ResistanceUses- Automotive Applications, TubingForms- PelletsProcessing-Extrusion, Injection MoldingInformation provided by Teknor Apex Company

Order this product through the following link:
http://www.lookpolymers.com/polymer_Teknor-Apex-Flexalloy-9300-70-Polyvinyl-Chloride-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.24 g/cc	1.24 g/cc	23Â°C; ASTM D792
Linear Mold Shrinkage	0.010 - 0.025 cm/cm	0.010 - 0.025 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	70	70	15 seconds; ASTM D2240
Tensile Strength, Yield	7.58 MPa	1100 psi	100%; ASTM D412
	16.4 MPa	2380 psi	ASTM D412
Elongation at Break	410 %	410 %	ASTM D412
Compression Set	29 %	29 %	73Â°F; ASTM D395

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-37.0 Â°C	-34.6 Â°F	ASTM D746

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	182 - 199 Â°C	360 - 390 Â°F	
Middle Barrel Temperature	182 - 199 Â°C	360 - 390 Â°F	
Front Barrel Temperature	182 - 199 Â°C	360 - 390 Â°F	
Mold Temperature	23.9 - 51.7 Â°C	75.0 - 125 Â°F	
Back Pressure	0.345 - 1.03 MPa	50.0 - 150 psi	

Descriptive Properties	Value	Comments
Screw Compression Ratio	2:1-3:1	
Screw L/D Ratio	20:1- 24:1	

Descriptive Properties	Value	Comments
------------------------	-------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China