

Teknor Apex Laripur® LPR 7560EG Thermoplastic Polyurethane

Category : Polymer , Thermoplastic , Polyurethane, TP

Material Notes:

Features: - Excellent performance under extreme and aggressive environments - Superior abrasion and cut resistance - Resistance to chemical, microbial attack and hydrolysis - Excellent flexibility at low temperatures - Good weathering properties - Non-halogen flame retardant - Glossy/Transparent - EEC Food Contact Approved - FDA Food Contact Approved - NSF 61 Portable Water Approved - USP Medical Class VI Applications: - Energy & Power Cables: coiled or spiral: Construction / Mining - Automotive Cables: Anti-lock Braking Systems - ABS - Industrial Cables: Traffic / Signal / Trains / Boats / Buildings - Geophysical Cables: Land & Off-shore; Marine, Sub-sea & Umbilical - Telecommunications Cables: Telephone & Data Transmission; Military and Fiber Optics - Audio and Medical Cables Information Provided by Teknor Apex

Order this product through the following link:

http://www.lookpolymers.com/polymer_Teknor-Apex-Laripur-LPR-7560EG-Thermoplastic-Polyurethane.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.10 g/cc	1.10 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	77	77	ASTM D2240
Tensile Strength	41.4 MPa	6000 psi	ASTM D412
Tensile Strength, Yield	3.03 MPa	440 psi	ASTM D412
	@Strain 50.0 %	@Strain 50.0 %	
	4.34 MPa	630 psi	
	@Strain 100 %	@Strain 100 %	ASTM D412
	8.27 MPa	1200 psi	ASTM D412
	@Strain 300 %	@Strain 300 %	ASTM D412
Elongation at Break	690 %	690 %	ASTM D412
Tear Strength	314 kN/m	1790 pli	ASTM D624

Thermal Properties	Metric	English	Comments
Vicat Softening Point	70.0 Â°C	158 Â°F	ASTM D1525

Optical Properties	Metric	English	Comments
Transmission, Visible	90 %	90 %	transparent; thickness not quantified

Descriptive Properties	Value	Comments
Abrasion Loss (mm3)	35	DIN 53516

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China