

Teknor Apex Monprene® MP-3955B Thermoplastic Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE

Material Notes:

Uses: Closures; Consumer Applications; Gaskets; Handles; Kitchenware; Medical/Healthcare Applications; Packaging; Safety Equipment; Sporting Goods; Toothbrush Handles; Tubing; Writing Instruments Forms: Pellets Processing Method: Extrusion; Injection Molding

Injection Notes: Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C); Injection Rate:

Fast Extrusion Notes: Screw Speed: 30 to 100 rpm Information Provided by Teknor Apex

Order this product through the following link:

http://www.lookpolymers.com/polymer_Teknor-Apex-Monprene-MP-3955B-Thermoplastic-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.18 g/cc	1.18 g/cc	ASTM D792
Melt Flow	14.0 g/10 min @Load 5.00 kg, Temperature 200 °C	14.0 g/10 min @Load 11.0 lb, Temperature 392 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	78	78	ASTM D2240
Tensile Strength at Break	11.7 MPa	1700 psi	ASTM D412
Elongation at Break	640 %	640 %	ASTM D412
Tear Strength	38.6 kN/m	220 pli	ASTM D624
Compression Set	35 % @Temperature 22.8 °C, Time 79200 sec	35 % @Temperature 73.0 °F, Time 22.0 hour	ASTM D395
	57 % @Temperature 70.0 °C, Time 79200 sec	57 % @Temperature 158 °F, Time 22.0 hour	ASTM D395

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-60.0 °C	-76.0 °F	ASTM D746

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	182 - 232 °C	360 - 450 °F	
Middle Barrel Temperature	188 - 238 °C	370 - 460 °F	

Front Barrel Temperature Processing Properties	193 - 243 Â°C Metric	380 - 470 Â°F English	Comments
Nozzle Temperature	199 - 249 Â°C	390 - 480 Â°F	
Zone 1	182 - 232 Â°C	360 - 450 Â°F	
Zone 2	188 - 238 Â°C	370 - 460 Â°F	
Zone 3	193 - 243 Â°C	380 - 470 Â°F	
Zone 5	199 - 249 Â°C	390 - 480 Â°F	
Die Temperature	199 - 249 Â°C	390 - 480 Â°F	
Melt Temperature	199 - 249 Â°C	390 - 480 Â°F	Processing Temperature
Mold Temperature	35.0 - 48.9 Â°C	95.0 - 120 Â°F	
Injection Pressure	1.38 - 5.52 MPa	200 - 800 psi	
Back Pressure	0.172 - 0.689 MPa	25.0 - 100 psi	
Cushion	0.381 - 2.54 cm	0.150 - 1.00 in	
Screw Speed	50 - 100 rpm	50 - 100 rpm	

Descriptive Properties	Value	Comments
Appearance	Opaque	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China