

Teknor Apex Sinpolene GPP5620 Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 20% Glass Fiber Filler

Material Notes:

Availability: Africa & Middle East; Latin America; Asia Pacific; South America Additive: Glass Fiber Reinforcement, 20% Filler by Weight

Features: Good Dimensional Stability; High Heat Resistance; Good Impact Resistance; Medium Rigidity Uses: Automotive Applications;

Housings; Pump Parts Appearance: Colors Available Forms: Pellets Processing Method: Injection Molding Information Provided by Teknor

Apex

Order this product through the following link:

http://www.lookpolymers.com/polymer_Teknor-Apex-Sinpolene-GPP5620-Polypropylene.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.03 g/cc	1.03 g/cc	ASTM D792
Linear Mold Shrinkage	0.0036 cm/cm	0.0036 in/in	ASTM D955
Linear Mold Shrinkage, Transverse	0.0077 cm/cm	0.0077 in/in	ASTM D955
Melt Flow	3.00 g/10 min @Load 2.16 kg, Temperature 230 Â°C	3.00 g/10 min @Load 4.76 lb, Temperature 446 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	50.0 MPa	7250 psi	ASTM D638
Elongation at Break	25 %	25 %	ASTM D638
Flexural Strength	55.0 MPa	7980 psi	ASTM D790
Flexural Modulus	2.45 GPa	355 ksi	ASTM D790
Izod Impact, Notched	2.40 J/cm @Temperature 22.8 Â°C	4.50 ft-lb/in @Temperature 73.0 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	150 Â°C	302 Â°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	121 Â°C @Thickness 3.20 mm	250 Â°F @Thickness 0.126 in	Unannealed; ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China