

Teknor Apex Sinpolene TPP2010 Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 10% Talc Filler

Material Notes:

Availability: Africa & Middle East; Latin America; Asia Pacific; South America Talc Filler, 10% Filler by Weight Uses: Appliance Components; Automotive Applications; Housings Forms: Pellets Processing Method: Injection Molding Information Provided by Teknor Apex

Order this product through the following link:

http://www.lookpolymers.com/polymer_Teknor-Apex-Sinpolene-TPP2010-Polypropylene.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.947 g/cc	0.947 g/cc	ASTM D792
Linear Mold Shrinkage	0.010 cm/cm	0.010 in/in	ASTM D955
Melt Flow	10.0 g/10 min @Load 2.16 kg, Temperature 230 Â°C	10.0 g/10 min @Load 4.76 lb, Temperature 446 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	30.0 MPa	4350 psi	ASTM D638
Elongation at Break	290 %	290 %	ASTM D412
Flexural Strength	36.0 MPa	5220 psi	ASTM D790
Flexural Modulus	1.60 GPa	232 ksi	ASTM D790
Izod Impact, Notched	0.747 J/cm @Temperature 22.8 Â°C	1.40 ft-lb/in @Temperature 73.0 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	118 Â°C	244 Â°F	Unannealed; ASTM D648
Vicat Softening Point	151 Â°C	304 Â°F	Loading 1 (10 N); ASTM D1525

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China