

Teknor Apex Sinvicomp SPF 3520 Polyvinyl Chloride, Flexible

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Flexible Grade

Material Notes:

Availability: Asia Pacific Features: High Stiffness Uses: Gaskets; Profiles; Seals Forms: Pellets Processing Method: Extrusion Information

Provided by Teknor Apex

Order this product through the following link:

http://www.lookpolymers.com/polymer_Teknor-Apex-Sinvicomp-SPF-3520-Polyvinyl-Chloride-Flexible.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.39 g/cc	1.39 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	94	94	ASTM D2240
Tensile Strength, Yield	18.6 MPa	2700 psi	9.8 in/min; ASTM D638
Elongation at Break	250 %	250 %	9.8 in/min; ASTM D638

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	190 °C	374 °F	
	@Time >=Error in fixSigDigits: @digits must be between 1 a sec	@Time >=Error in fixSigDigits: @digits must be between 1 a hour	Congo Red; BS 2782

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China