

Teknor Apex Telcar® TL-3050-88 Thermoplastic Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE

Material Notes:

Temperature Ratings: Wet Location: 75°C, Dry Location: 90°C Processing Method: Extrusion Information Provided by Teknor Apex

Order this product through the following link:

http://www.lookpolymers.com/polymer_Teknor-Apex-Telcar-TL-3050-88-Thermoplastic-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.900 g/cc	0.900 g/cc	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	88	88	
Tensile Strength	12.4 MPa	1800 psi	
Elongation at Break	750 %	750 %	

Thermal Properties	Metric	English	Comments
Brittleness Temperature	<= -50.0 °C	<= -58.0 °F	ASTM D746
Flammability, UL94	HB	HB	
Oxygen Index	17 %	17 %	ASTM D2863

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China