

Teknor Apex Telcar® TL-90-T707E-100 BLK 111 Thermoplastic Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE

Material Notes:

Uses: Automotive Applications; Automotive Exterior Parts; Automotive Exterior Trim; Automotive Interior Parts; Blow Molding Applications;

General Purpose; Grommets; Weatherstripping Forms: Pellets Processing Method: Extrusion; Injection Molding Injection Notes: Injection

Rate: Moderate-Fast Extrusion Notes: Screw Speed: 30 to 100 rpm Information Provided by Teknor Apex

Order this product through the following link:

http://www.lookpolymers.com/polymer_Teknor-Apex-Telcar-TL-90-T707E-100-BLK-111-Thermoplastic-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.980 g/cc	0.980 g/cc	ASTM D792
Melt Flow	5.80 g/10 min	5.80 g/10 min	ASTM D1238
	@Load 2.16 kg, Temperature 230 °C	@Load 4.76 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	50	50	10 seconds; ASTM D2240
	55	55	ASTM D2240
Tensile Strength at Break	17.5 MPa	2540 psi	ASTM D412
Tensile Stress	9.65 MPa	1400 psi	ASTM D412
	@Strain 100 %	@Strain 100 %	
	9.93 MPa	1440 psi	ASTM D412
	@Strain 300 %	@Strain 300 %	
Elongation at Break	720 %	720 %	ASTM D412

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	ASTM D257

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	171 - 193 °C	340 - 380 °F	
Middle Barrel Temperature	177 - 199 °C	350 - 390 °F	
Front Barrel Temperature	182 - 204 °C	360 - 400 °F	
Nozzle Temperature	188 - 210 °C	370 - 410 °F	

Zone 1 Processing Properties	166 - 188 °C Metric	330 - 370 °F English	Comments
Zone 2	171 - 193 °C	340 - 380 °F	
Zone 3	177 - 199 °C	350 - 390 °F	
Zone 5	182 - 204 °C	360 - 400 °F	
Die Temperature	190 - 210 °C	374 - 410 °F	
Melt Temperature	188 - 210 °C	370 - 410 °F	Processing Temperature
Mold Temperature	25.0 - 65.6 °C	77.0 - 150 °F	
Injection Pressure	1.38 - 6.89 MPa	200 - 1000 psi	
Back Pressure	0.172 - 0.345 MPa	25.0 - 50.0 psi	
Cushion	0.381 - 2.54 cm	0.150 - 1.00 in	
Screw Speed	50 - 100 rpm	50 - 100 rpm	

Descriptive Properties	Value	Comments
Appearance	Translucent	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China