

Teknor Apex Uniprene® UN-1069E2 Thermoplastic Vulcanizate

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Vulcanizate Elastomer (TPV)

Material Notes:

Notes: Injection Rate: Fast Uses: Expansion Joint; Grommets; Tubing; Gaskets; Plugs; Weatherstripping; Glazing; Shock Absorbing Pads

Forms: Pellets Processing Method: Extrusion; Injection Molding Extrusion Notes: Screw Speed: 30 to 100 rpm Information Provided by

Teknor Apex

Order this product through the following link:

http://www.lookpolymers.com/polymer_Teknor-Apex-Uniprene-UN-1069E2-Thermoplastic-Vulcanizate.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.00 g/cc	1.00 g/cc	ASTM D792
Melt Flow	3.00 g/10 min	3.00 g/10 min	ASTM D1238
	@Load 5.00 kg, Temperature 230 °C	@Load 11.0 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	69	69	ASTM D2240
Tensile Strength at Break	9.10 MPa	1320 psi	ASTM D412
Elongation at Break	350 %	350 %	ASTM D412

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	173 - 213 °C	344 - 416 °F	
Middle Barrel Temperature	179 - 219 °C	354 - 426 °F	
Front Barrel Temperature	184 - 224 °C	364 - 436 °F	
Nozzle Temperature	190 - 230 °C	374 - 446 °F	
Zone 1	166 - 204 °C	330 - 400 °F	
Zone 2	171 - 210 °C	340 - 410 °F	
Zone 3	177 - 216 °C	350 - 420 °F	
Zone 5	182 - 221 °C	360 - 430 °F	
Die Temperature	190 - 227 °C	374 - 440 °F	
Melt Temperature	190 - 230 °C	374 - 446 °F	Processing Temperature
Mold Temperature	35.0 - 60.0 °C	95.0 - 140 °F	

Injection Pressure Processing Properties	1.38 - 6.89 MPa Metric	200 - 1000 psi English	Comments
Back Pressure	0.172 - 0.862 MPa	25.0 - 125 psi	
Cushion	0.381 - 2.54 cm	0.150 - 1.00 in	
Screw Speed	50 - 120 rpm	50 - 120 rpm	

Descriptive Properties	Value	Comments
Appearance	Opaque	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China