

ThyssenKrupp XAR® 550 Structural Steel

Category: Metal, Ferrous Metal, Carbon Steel, Low Carbon Steel

Material Notes:

This Material Specification applies to 4 to 100 mm thick plates of the wear-resistant special structural steel XAR® 550.Application: The steel may be used for wear exposed structures, e.g. excavating, mining and earth-moving machinery, truck dump bodies, conveying, crushing and pulverizing equipment and scrap presses.Information Provided by Thyssen Krupp

Order this product through the following link:

http://www.lookpolymers.com/polymer_ThyssenKrupp-XAR-550-Structural-Steel.php

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	1800 MPa	261000 psi	
Tensile Strength, Yield	1500 MPa	218000 psi	
Elongation at Break	8.0 %	8.0 %	
Charpy Impact	22.0 J	16.2 ft-lb	
	@Temperature -40.0 °C	@Temperature -40.0 °F	

Component Elements Properties	Metric	English	Comments
Aluminum, Al	<= 1.3 %	<= 1.3 %	
Boron, B	<= 0.0050 %	<= 0.0050 %	
Carbon, C	<= 0.35 %	<= 0.35 %	
Chromium, Cr	<= 1.3 %	<= 1.3 %	
Manganese, Mn	<= 1.5 %	<= 1.5 %	
Molybdenum, Mo	<= 0.50 %	<= 0.50 %	
Nickel, Ni	<= 1.5 %	<= 1.5 %	
Phosphorous, P	<= 0.025 %	<= 0.025 %	
Silicon, Si	<= 0.80 %	<= 0.80 %	
Sulfur, S	<= 0.012 %	<= 0.012 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842



Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China