

## ThyssenKrupp XAR® PLUS Structural Steel

Category: Metal, Ferrous Metal, Carbon Steel, Low Carbon Steel

## **Material Notes:**

This Material Specification applies to 3 to 100 mm thick plates of the wear-resistant special structural steel XAR® PLUS.Application: The steel may be used for wear exposed structures, e.g. excavating, mining and earth-moving machinery, truck dump bodies, conveying, crushing and pulverizing equipment, scrap presses and paving moulds.Information Provided by Thyssen Krupp

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_ThyssenKrupp-XAR-PLUS-Structural-Steel.php

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	1350 MPa	196000 psi	
Tensile Strength, Yield	1200 MPa	174000 psi	
Elongation at Break	10 %	10 %	
Charpy Impact	30.0 J	22.1 ft-lb	
	@Temperature -40.0 °C	@Temperature -40.0 °F	

Component Elements Properties	Metric	English	Comments
Aluminum, Al	<= 1.3 %	<= 1.3 %	
Boron, B	<= 0.0050 %	<= 0.0050 %	
Carbon, C	<= 0.22 %	<= 0.22 %	
Chromium, Cr	<= 1.3 %	<= 1.3 %	
Copper, Cu	<= 0.30 %	<= 0.30 %	
Manganese, Mn	<= 1.5 %	<= 1.5 %	
Molybdenum, Mo	<= 0.50 %	<= 0.50 %	
Other	<= 0.55 %	<= 0.55 %	Carbon Equivalent
Phosphorous, P	<= 0.025 %	<= 0.025 %	
Silicon, Si	<= 0.80 %	<= 0.80 %	
Sulfur, S	<= 0.012 %	<= 0.012 %	

## **Contact Songhan Plastic Technology Co.,Ltd.**

Website: www.lookpolymers.com Email: sales@lookpolymers.com



Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China