

Tisan TISARBON® 10% Glass Fiber Reinforced Polycarbonate

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, 10% Glass Filled

Material Notes:

TISARBON has a wide area of application in construction, building auxiliary materials, electric/electronic, lighting equipment, home appliances, automotive, telecommunication and health products industries. General Specifications include: High temperature resistanceDimensional stabilityImpact resistanceExcellent surface qualityHigh light transparenceFlame resistanceLow moisture ratioToughness TISARBON has good chemical resistance against weak acids. It has medium resistance against alcohols, hydrocarbons, and engine fuels, and weak resistance against acids, alkalis, and organic solvents.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Tisan-TISARBON-10-Glass-Fiber-Reinforced-Polycarbonate.php

Physical Properties	Metric	English	Comments
Density	1.25 g/cc	0.0452 lb/in³	ISO 1183
Linear Mold Shrinkage	0.0040 cm/cm	0.0040 in/in	
Ash	10 %	10 %	ISO 3451

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	60.0 MPa	8700 psi	ISO 527-2
Tensile Strength, Yield	60.0 MPa	8700 psi	ISO 527-2
Elongation at Break	7.0 %	7.0 %	ISO 527-2
Elongation at Yield	5.0 %	5.0 %	ISO 527-2
Modulus of Elasticity	3.40 GPa	493 ksi	ISO 527-2
Izod Impact, Notched (ISO)	8.00 kJ/m²	3.81 ft-lb/in²	ISO 180

Thermal Properties	Metric	English	Comments
Melting Point	230 °C	446 °F	
Vicat Softening Point	141 °C	286 °F	ISO 306
Heat Distortion Temperature	140 °C	284 °F	ISO 75-2
Flammability, UL94	V-0	V-0	
Glow Wire Test	960 °C	1760 °F	60695-2-10

Electrical Properties	Metric	English	Comments
Comparative Tracking Index	175 V	175 V	TS EN 60112

Electrical Properties	Metric	English	Comments
Processing Properties	Metric	English	Comments
Feed Temperature	70.0 °C	158 °F	
Rear Barrel Temperature	280 - 290 °C	536 - 554 °F	Aft-1. Region Temperature
Middle Barrel Temperature	270 - 280 °C	518 - 536 °F	Mid-2. Region Temperature
Front Barrel Temperature	260 - 270 °C	500 - 518 °F	Pre-3. Region Temperature
Nozzle Temperature	280 - 290 °C	536 - 554 °F	
Melt Temperature	270 - 290 °C	518 - 554 °F	
Drying Temperature	90.0 - 120 °C	194 - 248 °F	Predrying Temperature
Dry Time	3 - 5 hour	3 - 5 hour	Predrying Time
Moisture Content	0.30 %	0.30 %	ISO 62

Descriptive Properties	Value	Comments
Block Temperature	80°C	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China