

Tisan TISESTER® 30% Glass Fiber Reinforced Heat Stabilized Copolymer Polybutylene Terephthalate

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), 30% Glass Fiber Filled

Material Notes:

TISESTER has a wide area of application in automotive, electric/electronics and durable goods industries. General Specifications include: Excellent surface appearance High corrosion and abrasion resistance Excellent toughness High temperature resistance Excellent chemical resistance Electrical isolation and arc resistance High performance Easy processability Fast cycle time Glass fiber reinforcement imparts high shrinkage resistance and impact resistance to TISESTER products, yielding improvements in thermal features as well. PBT is resistant against solvents, exhibits low shrinkage during shaping, and it is mechanically strong, heat resistant for temperatures up to 150°C, and can be reinforced for flame retardance. Tisester compounds display sufficient resistance against hydrocarbons, alcohols, ethers, acids, and alkali solvents.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Tisan-TISESTER-30-Glass-Fiber-Reinforced-Heat-Stabilized-Copolymer-Polybutylene-Terephthalate.php

Physical Properties	Metric	English	Comments
Density	1.51 g/cc	0.0546 lb/in ³	ISO 1183
Linear Mold Shrinkage	0.0030 cm/cm	0.0030 in/in	
Ash	30 %	30 %	ISO 3451

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	84	84	ISO 868
Tensile Strength at Break	157 MPa	22800 psi	ISO 527-2
Tensile Strength, Yield	155 MPa	22500 psi	ISO 527-2
Elongation at Break	2.9 %	2.9 %	ISO 527-2
Elongation at Yield	2.7 %	2.7 %	ISO 527-2
Modulus of Elasticity	9.50 GPa	1380 ksi	ISO 527-2
Izod Impact, Notched (ISO)	8.50 kJ/m ²	4.04 ft-lb/in ²	ISO 180

Thermal Properties	Metric	English	Comments
Melting Point	225 - 230 °C	437 - 446 °F	
Vicat Softening Point	215 °C	419 °F	ISO 306
Heat Distortion Temperature	214 °C	417 °F	ISO 75-2
Flammability, UL94	HB	HB	

Thermal Properties	Metric	English	Comments
Glow Wire Test	750 °C	1380 °F	60695-2-10

Electrical Properties	Metric	English	Comments
Comparative Tracking Index	400 V	400 V	TS EN 60112

Processing Properties	Metric	English	Comments
Feed Temperature	70.0 °C	158 °F	
Rear Barrel Temperature	220 - 250 °C	428 - 482 °F	Aft-1. Region Temperature
Middle Barrel Temperature	220 - 250 °C	428 - 482 °F	Mid-2. Region Temperature
Front Barrel Temperature	220 - 250 °C	428 - 482 °F	Pre-3. Region Temperature
Nozzle Temperature	225 °C	437 °F	
Melt Temperature	220 - 230 °C	428 - 446 °F	
Drying Temperature	110 - 120 °C	230 - 248 °F	Predrying Temperature
Dry Time	4 - 5 hour	4 - 5 hour	Predrying Time
Moisture Content	0.20 %	0.20 %	ISO 62

Descriptive Properties	Value	Comments
Block Temperature	80°C	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China