

Total Evatane® 28 - 05 HDPE vinyl acetate copolymer, blown film, injection molding (discontinued **)

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Film Grade

Material Notes:

EVA Copolymer made by high pressure tubular process. Temperature profile (°C) for injection molding: 120 to 150. Information provided provided by Total Petrochemicals. Total Petrochemicals includes former Fina and Atofina plastics product lines.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Total-Evatane-28-05-HDPE-vinyl-acetate-copolymer-blown-film-injection-molding-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.950 g/cc	0.0343 lb/in ³	ISO 1183
Melt Flow	7.0 g/10 min	7.0 g/10 min	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	28	28	ISO 868
Tensile Strength at Break	33.0 MPa	4790 psi	ISO 527
Elongation at Break	850 %	850 %	ISO 527
Modulus of Elasticity	0.0200 GPa	2.90 ksi	ISO 5527
Dart Drop Test	>= 1000 g	>= 2.20 lb	50µ; ISO 7765-1

Thermal Properties	Metric	English	Comments
Melting Point	72.0 °C	162 °F	ISO 11357-3
Vicat Softening Point	41.0 °C	106 °F	ISO 306

Descriptive Properties	Value	Comments
Food Status	This material conforms to both European and American Food contact regulations.	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China