

Total LDPE 1022 FH 24 Low Density Polyethylene - Blown Film

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , LDPE , Low Density Polyethylene (LDPE), Film Grade

Material Notes:

LDPE 1022 FH 24 is a low density polyethylene made by a high pressure process. LDPE 1022 FH 24 is a slip and anti-block formulated grade. LDPE 1022 FH 24 is suited to many applications in the field of consumer, industrial, food or hygiene packaging such as bags, lamination and coextrusion film. Information provided by Total Petrochemicals.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Total-LDPE-1022-FH-24-Low-Density-Polyethylene-Blown-Film.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.923 g/cc	0.923 g/cc	ISO 1183
Thickness	40.0 microns	1.57 mil	for samples tested on this data sheet
	20.0 - 150 microns	0.787 - 5.91 mil	possible range, depending on extrusion conditions
Melt Flow	2.3 g/10 min @Load 2.16 kg, Temperature 190 °C	2.3 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133
Antiblock Level	750 ppm	750 ppm	Talc
Slip Level	750 ppm	750 ppm	Erucamide

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	12.0 MPa	1740 psi	ISO 527-3
Film Tensile Strength at Yield, TD	11.5 MPa	1670 psi	ISO 527-3
Film Elongation at Break, MD	350 %	350 %	ISO 527-3
Film Elongation at Break, TD	580 %	580 %	ISO 527-3
Elmendorf Tear Strength, MD	7.30 g/micron	185 g/mil	ISO 6383-2
Elmendorf Tear Strength, TD	6.10 g/micron	155 g/mil	ISO 6383-2
Dart Drop Test	95.0 g	0.209 lb	ISO 7765-1
Film Tensile Strength at Break, MD	22.0 MPa	3190 psi	ISO 527-3
Film Tensile Strength at Break, TD	20.0 MPa	2900 psi	ISO 527-3

Thermal Properties	Metric	English	Comments
Melting Point	109 °C	228 °F	ISO 11357

Thermal Properties	Metric	English	Comments
Optical Properties	Metric	English	Comments
Haze	8.0 %	8.0 %	ISO 14782
Processing Properties	Metric	English	Comments
Processing Temperature	150 - 190 °C	302 - 374 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China