

Total PPR 3260 Random Copolymer Polypropylene, Extrusion Grade

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Extrusion Grade

Material Notes:

Polypropylene PPR 3260 is a random copolymer polypropylene with a melt flow index of 1.8 g/10 min suitable for extrusion applications. Information provided by Total Petrochemicals.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Total-PPR-3260-Random-Copolymer-Polypropylene-Extrusion-Grade.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.902 g/cc	0.902 g/cc	ISO 1183
Bulk Density	0.525 g/cc	0.0190 lb/in ³	ISO 1183
Melt Flow	1.8 g/10 min @Load 2.16 kg, Temperature 230 °C	1.8 g/10 min @Load 4.76 lb, Temperature 446 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	84	84	ISO 2039-2
Tensile Strength, Yield	26.0 MPa	3770 psi	ISO 572-2
Elongation at Yield	10 %	10 %	ISO 572-2
Tensile Modulus	1.10 GPa	160 ksi	ISO 572-2
Flexural Modulus	1.00 GPa	145 ksi	ISO 178
Izod Impact, Notched (ISO)	7.50 kJ/m ²	3.57 ft-lb/in ²	ISO 180
Charpy Impact, Notched	0.850 J/cm ²	4.04 ft-lb/in ²	ISO 179

Thermal Properties	Metric	English	Comments
Melting Point	148 °C	298 °F	ISO 3146
Vicat Softening Point	67.0 °C @Load 5.10 kg	153 °F @Load 11.2 lb	50°C per hour; ISO 306
	130 °C @Load 1.02 kg	266 °F @Load 2.25 lb	50°C per hour; ISO 306

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China